

(19)



(11)

EP 0 978 766 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
21.03.2007 Bulletin 2007/12

(51) Int Cl:
G03G 9/087^(2006.01) G03G 9/08^(2006.01)
G03G 9/12^(2006.01)

(21) Application number: **97949243.6**

(86) International application number:
PCT/JP1997/004848

(22) Date of filing: **25.12.1997**

(87) International publication number:
WO 1998/029783 (09.07.1998 Gazette 1998/27)

(54) **TONER FOR ELECTROSTATIC IMAGE DEVELOPMENT CONTAINING POLYOLEFIN RESIN
HAVING CYCLIC STRUCTURE**

TONER FÜR DIE ELEKTROSTATISCHE BILDENTWICKLUNG, DER CYCLISCHE
POLYOLEFINHARZE ENTHÄLT

TONER POUR DEVELOPPEMENT D'IMAGE ELECTROSTATIQUE, CONTENANT DE LA RESINE
A BASE DE POLYOLEFINE A STRUCTURE CYCLIQUE

(84) Designated Contracting States:
BE DE FR GB IT NL

(30) Priority: **26.12.1996 JP 34854696**

(43) Date of publication of application:
09.02.2000 Bulletin 2000/06

(73) Proprietor: **Topas Advanced Polymers GmbH**
65926 Frankfurt am Main (DE)

(72) Inventors:

- **NISHIOKA, Toshimi**
Osaka 565-0854 (JP)
- **FUKUZAWA, Junichi,**
25-7, Matsukazedai
Kanagawa 227-0067 (JP)
- **NAKAMURA, Toru**
Abiko-shi
Chiba 270-1164 (JP)
- **ARAI, Satoshi**
Tokyo 133-0052 (JP)
- **HOGA, Takuya**
Saitama 336-0932 (JP)

- **ARAI, Masayuki**
Saitama 361-0037 (JP)
- **LAND, Horst-Tore**
D-65719 Hofheim (DE)
- **OSAN, Frank**
D-65779 Kelkheim in Taunus (DE)
- **WEHRMEISTER, Thomas**
D-6528 Rüsselsheim (DE)

(74) Representative: **Ackermann, Joachim**
Postfach 11 13 26
60048 Frankfurt am Main (DE)

(56) References cited:

JP-A- 6 019 220	JP-A- 6 027 714
JP-A- 6 041 402	JP-A- 6 214 431
JP-B- 46 006 157	US-A- 5 106 715

- **PATENT ABSTRACTS OF JAPAN vol. 14, no. 465**
(P-1114), 9 October 1990 (1990-10-09) & JP 02
184864 A (RICOH), 19 July 1990 (1990-07-19)
- **PATENT ABSTRACTS OF JAPAN vol. 7, no. 270**
(P-240), 2 December 1983 (1983-12-02) & JP 58
149060 A (NIPPON ZEON), 5 September 1983
(1983-09-05)

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 0 978 766 B1

Description

[Field of Utilization in Industry]

5 **[0001]** The present invention relates to a toner for development of an electrostatically charged image. More specifically, this invention relates to a dry one-component magnetic toner, a dry one-component nonmagnetic toner, a dry two-component toner or a dry polymerized toner which, when fixed, is excellent in anti-spent toner effect, and can a well fixed, highly transparent, sharp image.

10 **[0002]** The invention also relates to the above-mentioned toner for use in copiers, printers, facsimile machines, color copiers, color laser copiers, color laser printers, and electrophotographic high speed printers.

[Prior Art]

15 **[0003]** Electrostatically charged image developing copiers and printers are gaining popularity because of widespread office automation. With this background, demand is growing for high grade or sharp copied images which are highly light transmissive and well fixed.

20 **[0004]** Under these circumstances, we stated to the following effect in Japanese Patent Application No. 354063/95 (filed December 29, 1995), which was not laid open to the public when the present application was filed: "The relevant problem can be solved or diminished by using a polyolefin resin of a cyclic structure as a binder resin for a toner for heat roller fixing type electrostatically charged image developing copiers and printers, and also by incorporating less than 50% by weight of the polyolefin resin with a high viscosity into the entire binder resin. As a result, a sharp, high quality copied image excellent in fixing, light transmission and anti-spent toner effect can be obtained. Particularly when this resin is used in a color toner, its characteristics are exhibited."

25 **[0005]** This previous invention, however, was defective in that it minimally gave a sufficiently broad offset-free temperature range suitable for practical use, and scarcely achieved full fixing at an even higher copying speed demanded by users.

30 **[0006]** In fixing a toner image onto plain paper or an OHP film, various fixing methods are available, such as hot roller fixing, hot belt fixing, pressure fixing, radiant heat fixing, or flash fixing. In recent years, energy saving symbolized by restriction has been demanded increasingly, and demand has become intense for a toner fixable at a low temperature and a low pressure. The thermal properties and mechanical properties of conventional styrene-acrylate resins and polyester resins, or the polyolefin resins of a cyclic structure described in Japanese Patent Application No. 354063/95 cannot satisfy the requirements at lower temperatures or pressures than the current level. Improvement in the thermal properties of these resins on one hand resulted in the deterioration of storage stability of the toner on the other hand.

35 **[0007]** General formulations for toners in electrostatically charged image developing copiers and printers are shown in Table 1.

Table 1 General Formulations of Toners

(Unit: % by weight)						
	Binder resin	Colorant	Charge control agent	Function imparting agent	Magnetic powder	Solvent
40 Dry two-component toner	50-100	0-20	0-10	0-20	-	-
45 Dry nonmagnetic one-component toner	50-100	0-20	0-10	0-20	-	-
50 Dry magnetic one-component toner	0-100	0-20	0-10	0-20	0-60	-
55 Dry polymerized toner	50-100	0-20	0-10	0-20		

EP 0 978 766 B1

(continued)

(Unit: % by weight)						
	Binder resin	Colorant	Charge control agent	Function imparting agent	Magnetic powder	Solvent
Liquid dried toner	15-50	0-10	0-5	0-10	-	50-70
Liquid toner	15-50	0-10	0-5	0-10	-	50-70

[Object to be Attained by the Invention]

[0008] The object of the present invention is to provide a toner in a dry two-component, dry nonmagnetic one-component, dry magnetic one-component or a dry polymerized toner developer which exhibits the effects achieved by Japanese Patent Application No. 354063/95, shows a sufficiently broad offset-free temperature range suitable for practical use, can attain sufficient fixing even by high speed copying, and gives a higher grade image, namely, a well fixed, highly optically transparent, sharp image in an electrostatically charged image developing copier or printer.

[Means for Attaining the Object]

[0009] The foregoing object is attained by using as a binder resin for a toner a binder resin which at least contains a polyolefin resin having a cyclic structure, the polyolefin resin having a cyclic structure being composed of a resin or resin fraction having a number average molecular weight (Mn), as measured by GPC, of less than 7,500 and a resin or resin fraction having said number average molecular weight of 7,500 or more; and in which in said polyolefin resin having a cyclic structure, a resin or resin fraction having an intrinsic viscosity (I.v.) of 0.25 dl/g or more, a heat distortion temperature (HDT) by the DIN 53461-B method of 70°C or higher, and a number average molecular weight (Mn) of 7,500 or more and a weight average molecular weight (Mw) of 15,000 or more, as measured by the GPC method, is contained in a proportion of less than 50% by weight based on the entire binder resin.

[0010] Thus, the invention concerns a toner for development of an electrostatically charged image, the toner consisting essentially of a binder resin, a colorant, a function imparting agent (generally, wax as a mold release agent), and a charge control agent, the binder resin at least containing the above-described polyolefin resin having a cyclic structure, the polyolefin resin satisfying the above conditions.

[0011] The polyolefin resin having a cyclic structure used herein is, for example, a copolymer of an α -olefin (broadly, an acyclic olefin), such as ethylene, propylene or butylene, with a cyclic and/or polycyclic compound having at least one double bond, such as cyclohexane or norbornene Tetracyclododecene (TCD) and Dicyclopentadiene (DCPD), the copolymer being colorless and transparent, and having high light transmission. This polyolefin resin having a cyclic structure is a polymer obtained, for instance, by a polymerization method using a metallocene catalyst or a Ziegler catalyst and catalyst for the metathesis polymerization, therefore double-bond-opening and ring-opening polymerization reactions.

[0012] Examples of synthesis of the polyolefin resin having a cyclic structure are disclosed in JP-A-339327/93, JP-A-9223/93, JP-A-271628/94, EP-A-203799, EP-A-407870, EP-A-283164, EP-A-156464 and JP-A-7253315.

According to these examples, the polyolefin resin is obtained by polymerizing optionally one acyclic olefin monomer with at least one cycloolefin monomer at a temperature of -78 to 150°C, preferably 20 to 80°C, and a pressure of 0.01 to 64 bars in the presence of a catalyst comprising at least one metallocene containing zirconium or hafnium together with a cocatalyst such as aluminoxane. Other useful polymers are described in EP-A-317262, hydrogenated polymers and copolymers of styrene and dicyclopentadiene are useful too.

[0013] When dissolved in an inert hydrocarbon such as an aliphatic or aromatic hydrocarbon, the metallocene catalyst is activated. Thus, the metallocene catalyst is dissolved, for example, in toluene for preliminary activation and reaction in the solvent.

[0014] The important properties of COC are softening point, melting point, viscosity, dielectric properties, anti off set window and transparency. The following adjustments can be carried out advantageously selection of monomers/comonomers, ratio of comonomers in copolymer, molecular weight, molecular weight distribution, hybrid polymers, blends and additives.

[0015] The molar ratio of the acyclic olefin and the cycloolefin charged for the reaction can be varied widely depending on the targeted polyolefin resin having a cyclic structure. This ratio is adjusted, preferably, to 50:1 to 1:50, more preferably 20:1 to 1:20.

[0016] When the copolymer components charged for the reaction are a total of two compounds, ethylene as the acyclic polyolefin and norbornene as the cycloolefin, the glass transition point (Tg) of the cyclic polyolefin resin as the reaction

EP 0 978 766 B1

product is influenced greatly by their charge proportions. When content of norbornene is increased, the Tg also tends to rise. When the proportion of norbornene charged is approximately 60% by weight, for instance, the Tg is about 60 to 70°C.

[0017] The physical properties, such as number average molecular weight are controlled as known from the literatures.

5 [0018] The colorless, transparent, highly light-transmissive polyolefin of a cyclic structure used in the present invention may be a mixture of a low-viscosity resin having a number average molecular weight, as measured by GPC, of less than 7,500, preferably 1,000 to less than 7,500, more preferably 3,000 to less than 7,500, a weight average molecular weight, as measured by GPC, of less than 15,000, preferably 1,000 to less than 15,000, more preferably 4,000 to less than 15,000, an intrinsic viscosity (i.v.) of less than 0.25 dl/g. Tg of preferably lower than 70°C, and a high-viscosity resin
10 having a number average molecular weight, as measured by GPC, of 7,500 or more, preferably 7,500 to 50,000, a weight average molecular weight, as measured by GPC, of 15,000 or more, preferably 50,000 to 500,000, an i.v. of 0.25 dl/g or more. Alternatively, the polyolefin resin may have a molecular weight distribution with a single peak, and contain a resin fraction having a number average molecular weight of less than 7,500 and a resin fraction having a number
15 average molecular weight of 7,500 or more. Alternatively, the polyolefin resin may have two or more peaks, in which its resin fraction having at least one of these peaks has a number average molecular weight of less than 7,500 and its resin fraction having the other peak has a number average molecular weight of 7,500 or more. The resin fractions mentioned here refer to respective resin components before mixing if the polyolefin resin having a cyclic structure is composed of a mixture of different components, such as those with various number average molecular weights; otherwise it refers to resin divisions formed by fractionating the final synthetic product by suitable means such as GPC. If these resin fractions
20 are monodisperse or close to monodisperse, Mn of 7,500 nearly corresponds to Mw of 15,000.

[0019] The high-molecular weight/low-molecular weight polyolefin resin having a cyclic structure has the above-mentioned number average molecular weights Mn, weight average molecular weights Mw, intrinsic viscosities i.v.. Thus, the Mw/Mn ratio, used as a measure of the degree of dispersion of molecular weight distribution, is as low as from 1 to 2.5, namely, a monodisperse or nearly monodisperse state. Thus, a toner having a quick heat response and a high fixing
25 strength can be produced. This polyolefin resin not only enables fixing at a low temperature and a low pressure, but also contributes to the storage stability, anti-spent toner effect, and electric stability properties such as uniform charge distribution or constant charging efficiency or static elimination efficiency. If the low viscosity resin, in particular, is monodisperse or nearly monodisperse, the resulting toner shows better heat response characteristics, such as instantaneous melting or setting behavior.

30 [0020] The high-viscosity/low-viscosity polyolefin resin having a cyclic structure, moreover, is colorless, transparent, and highly light-transmissive. For instance, the azo pigment Permanent Rubi F6B (Hoechst AG) was added to the resin, and the mixture was thoroughly kneaded, and then formed into a sheet by means of a press. This sheet was confirmed to be highly transparent. Thus, the resin is sufficiently usable for a color toner. Measurement by the DSC method has shown this polyolefin resin to require a very low heat of fusion. Hence, this resin can be expected to markedly
35 reduce energy consumption for fixing.

[0021] The high-viscosity polyolefin resin having a cyclic structure also has the above-mentioned properties; thus, as contrasted with the low-viscosity polyolefin resin, it imparts structural viscosity to the toner, thereby improving the offset preventing effect and the adhesion to a copying medium such as paper or film.

40 [0022] If the amount of the high-viscosity resin used is 50% by weight or more based on the entire binder resin, the uniform kneading properties extremely decline, impeding the toner performance. That is, a high grade image, i. e., a sharp image with high fixing strength and excellent heat response, cannot be obtained.

[0023] The toner for development of an electrostatically charged image according to the present invention has the binder resin at least containing the polyolefin resin of a cyclic structure, in which the polyolefin resins having low viscosity and high viscosity are used as the polyolefin resin. Hence, the offset-free temperature range covers the high temperature
45 side and the low temperature side, the fixing properties by high speed copying are enhanced, and the fixing properties at low temperatures and low pressures are both improved.

[0024] To broaden the offset-free temperature range to the low temperature side, the low viscosity polyolefin resin with a number average molecular weight of less than 7,500 contributes. To broaden the offset-free temperature range to the high temperature side, on the other hand, the high viscosity polyolefin resin with a number average molecular weight of 7,500 or more contributes. In order to broaden the offset-free temperature range to the high temperature side more effectively, it is preferred for the high viscosity polyolefin resin with a number average molecular weight of 20,000 or more to be present. The proportions of the cyclic structure polyolefin resins with number average molecular weights of less than 7,500 and 7,500 or more contained in the entire binder resin are each preferably 0.5 part by weight or more, more preferably 5 parts by weight or more, based on 100 parts by weight of the entire binder resin. If the content of each
50 polyolefin resin is less than 0.5 part by weight, it is difficult to obtain a practical broad offset-free temperature range.

55 [0025] In the case of the polyolefin resin of a cyclic structure composed of the low viscosity polyolefin resin with a number average molecular weight of less than 7,500 and the high viscosity polyolefin resin with a number average molecular weight of 25,000 or more, a medium viscosity polyolefin resin of a cyclic structure with a number average

EP 0 978 766 B1

molecular weight of 7,500 or more but less than 25,000 is added to enhance the compatibility of these low and high viscosity polyolefin resin components. This addition has been found effective in bringing an offset-free range continuously.

[0026] In other words; the binder resin at least containing a polyolefin resin of a cyclic structure, the polyolefin resin comprising resins or resin fractions having three molecular weight ranges expressed by number average molecular weight (Mn), as measured by GPC, of less than 7,500, 7,500 or more but less than 25,000, and 25,000 or more is also an advantageous embodiment of the present invention. The resin fractions constituting the respective molecular weight ranges may be a resin having a molecular weight distribution with one or two peaks that can be divided into fractions with the three molecular weight ranges expressed as Mn. Alternatively, the resin fractions constituting the respective molecular weight ranges may be a mixture of resins having molecular weight distributions with three or more peaks that have at least one molecular weight peak in each of the above molecular weight ranges.

[0027] The proportion of the medium viscosity polyolefin resin or resin fraction for increasing compatibility is preferably 1 part by weight or more, more preferably 5 parts by weight or more, based on 100 parts by weight of the binder resin.

[0028] In the present invention, a toner using as a binder resin a mixture of the polyolefin resin, composed of resins or resin fractions with Mn of less than 7,500 and Mn of 7,500 or more, and other resin also realizes a high grade image, i.e., a high fixing strength sharp image. The other resin refers to one of a polyester resin, an epoxy resin, a polyolefin resin, a vinyl acetate resin, a vinyl acetate copolymer resin, a styrene-acrylate resin and other acrylate resin, or a mixture or a hybrid polymers of any of the mentioned polyolefin. The proportions of the polyolefin resin having a cyclic structure and the other resin used in the binder resin are 1 to 100, preferably 20 to 90, more preferably 50 to 90 parts by weight of the former, and 99 to 0, preferably 80 to 10, more preferably 50 to 10 parts by weight of the latter, based on 100 parts by weight of the binder resin. If the amount of the former resin is less than 1 part by weight, it becomes difficult to obtain a high grade image.

[0029] By introducing carboxyl groups into the polyolefin resin having a cyclic structure, its compatibility with the other resin and the dispersibility of the pigment can be improved. Furthermore, the adhesion to paper or film, a copying medium, can be enhanced, leading to increased fixability. Two-stage reaction method of polymerizing the polyolefin resin having a cyclic structure first, and introducing carboxyl groups subsequently is preferred.

[0030] At least two methods are available for introducing the carboxyl groups into the resin. One is a method of oxidizing an alkyl group, such as methyl, at the end of the resin by the fusing air oxidation method to convert it into a carboxyl group. With this method, however, the polyolefin resin of a cyclic structure that has been synthesized using a metallocene catalyst has few branches, making it difficult to introduce many carboxyl groups into this resin. The other method is to add a peroxide to the resin, and react maleic anhydride or other ester and ester derivatives, amides and other polar unsaturated compounds with the resulting radical portion. With this method, it is theoretically possible to introduce many carboxyl groups onto the resin, but an increased proportion of introduction results in yellowing of the resin, making its transparency poor. If the use of the product is restricted to a toner, therefore, it is preferred to introduce 1 to 15% by weight, based on the resin, of maleic anhydride. The same improvement can be achieved by introducing hydroxyl groups or amino groups by a known method.

[0031] To improve the fixability of the toner, a crosslinked structure may be introduced into the polyolefin resin having a cyclic structure. One of the methods for introducing this crosslinked structure is to add a diene monomer, such as norbornadiene or cyclohexadiene, together with the acyclic olefin and the cycloolefin, followed by reacting the system, thereby obtaining a terpolymeric polyolefin having a cyclic structure. As a result of this method, the resin has a terminal showing activity even without a crosslinking agent. A known chemical reaction such as oxidation or epoxidation, or the addition of a crosslinking agent to form a crosslinked structure, results in the functioning of the resin.

[0032] Another method is to add a metal such as zinc, copper or calcium to the polyolefin resin of a cyclic structure having carboxyl groups introduced therein, and then blend and melt the mixture with a screw or the like to disperse the metal uniformly as fine particles in the resin, thereby forming an ionomer having a crosslinked structure. Concerning a technology on such an ionomer, United States Patent No. 4,693,941, for example, discloses a terpolymer of ethylene containing carboxyl groups which may take the form of a divalent metal salt upon partial or complete neutralization in an attempt to obtain toughness. Officially Published Patent Gazette No. 500348/94 reports a polyester resin molded product containing an ionomer of an unsaturated carboxylic acid that has about 20 to 80% of the carboxylic acid groups neutralized with zinc, cobalt, nickel, aluminum or copper (II), the product intended for the same purpose.

[0033] The toner of the present invention uses a known function imparting agent to enhance the offset preventing effect. To improve this performance further, the addition of wax has been found effective. As a polar wax, at least one wax selected from amide wax, carnauba wax, higher fatty acids and their esters, higher fatty acid metallic soaps, partially saponified higher fatty acid esters, and higher aliphatic alcohols can be used as the function imparting agent. As a nonpolar wax, at least one wax selected from polyolefin wax and paraffin wax can be used as the function imparting agent.

[0034] The polar wax may work as an external lubricant for the polyolefin resin, a nonpolar resin, because of the difference between polarity and nonpolarity. The nonpolar wax may work as an external lubricant mainly because of easy surface migration due to its low molecular weight, contributing to improved offset-free properties.

[0035] The toner for development of an electrostatically charged image according to the present invention can be

EP 0 978 766 B1

obtained by adding a colorant, a charge control agent, a function imparting agent, and if desired, other additives to the aforementioned binder resin, and performing known methods such as extrusion, kneading, grinding and classification. A flowing agent and a lubricant are further added.

[0036] The colorant may be a known one, such as carbon black, diazo yellow, phthalocyanine blue, quinacridone, carmine 6B, monoazo red or perylene.

[0037] Examples of the charge control agent are known ones such as Nigrosine dyes, fatty acid modified Nigrosine dyes, metallized Nigrosine dyes, metallized fatty acid modified Nigrosine dyes, chromium complexes of 3,5-di-tert-butylsalicylic acid, quaternary ammonium salts, triphenylmethane dyes, and azochromium complexes.

[0038] To the toner of the present invention, there may be further added a flowing agent such as colloidal silica, aluminum oxide or titanium oxide, and a lubricant comprising a fatty acid metal salt such as barium stearate, calcium stearate or barium laurate.

[0039] The toner of the present invention can be used as a dry one-component magnetic toner, a dry one-component nonmagnetic toner, a dry two-component toner, or a dry polymerized toner.

This invention is applicable to a copier, a printer, a facsimile machine and an electrophotographic high speed printer.

The invention is also applicable as a full-color toner in a color copier, a color laser copier and a color laser printer.

[Examples]

[0040] The present invention will be described in more detail by reference to Examples and Comparative Examples.

[0041] The physical properties of the polyolefin resin having a cyclic structure used in the invention are measured by the following methods:

GPC conditions for measurement of molecular weight

[0042]

Molecular weight conversion method:

Standard polyethylene used.

Column used: JORDI-SAEULE 500x10 LINEAR

Mobile phase: 1,2-dichlorobenzene (135°C)

(flow rate 0.5 ml/min)

Detector: Differential refractometer

Method for measurement of intrinsic viscosity:

Inherent viscosity at 135°C when 1.0 g of the resin was uniformly dissolved in 100 ml of decalin

<Toner preparation method 1>

Dry nonmagnetic one component system and dry two component system:

[0043] One % by weight of a charge control agent (Copy Charge NX, Hoechst), 4% by weight of amide wax (BNT, Nippon Seika), 0.5% by weight of aerosol silica (HDK-H2000, Wacker Chemie), 5% by weight of magenta pigment (Permanent Rubin F6B, Hoechst) as a colorant, and 89.5% by weight of a binder resin were mixed, and melt kneaded at 130°C by a twin roll. Then, the mixture was cooled to solidification, and coarsely crushed, followed by finely dividing the particles using a jet mill. The resulting fine particles were classified to select particles with an average particle diameter of about 10 µm, thereby preparing a toner.

<Toner preparation method 2>

Dry magnetic one component system:

[0044] Forty % by weight of a magnetic powder (BL100, Titanium Industry), 1% by weight of a charge control agent (Copy Charge NX, Hoechst), 4% by weight of wax (BNT, Nippon Seika), 0.5% by weight of aerosol silica (HDK-H2000, Wacker Chemie), 2.0% by weight of calcium carbonate (Shiraishi Calcium) as an extender pigment and a structural viscosity improver, and 52.5% by weight of a binder resin were mixed, and melt kneaded at 150°C by a twin roll. Then, the mixture was cooled to coagulation, and coarsely ground, followed by finely dividing the particles using a jet mill. The resulting fine particles were classified to select particles with an average particle diameter of about 10 µm, thereby preparing a toner.

EP 0 978 766 B1

<Toner preparation method 3>

Dry polymerized system:

[0045] One % by weight of a charge control agent (Copy Charge NX, Hoechst), 4% by weight of wax (BNT, Nippon Seika), 0.5% by weight of aerosol silica (HDK-H2000, Wacker Chemie), and 5% by weight of magenta pigment (Permanent Rubin F6B, Hoechst) as a colorant were mechanically dispersed and mixed in monomer components corresponding to 89.5% by weight of a binder resin at the time of polymerization of the binder resin. The mixture was interfacially polymerized into particles with an average particle diameter of about 10 μm , thereby preparing a toner.

Table 1

Ex. or Comp. Ex. No.	Toner preparation method	Formulation of binder resin			
		Sample No. Weight %		Sample No. Weight %	
Ex. 1	1 and 3	1	89.5	-	-
Ex. 2	1 and 3	1	60	2	29.5
Ex. 3	1 and 3	1	60	7	29.5
Ex. 4	1 and 3	3	60	-	-
Ex. 5	1 and 3	3	89.5	7	29.5
Ex. 6	1 and 3	5	60	-	-
Ex. 7	1 and 3	5	60	7	29.5
Ex. 8	1 and 3	1	60	2	14.5
				9	15
Ex. 9	2	1	52.5	-	-
Ex. 10	2	1	30	2	22.5
Ex. 11	2	1	30	7	22.5
Ex. 12	2	1	30	8	22.5
Ex. 13	2	3	52.5	-	-
Ex. 14	2	3	30	7	22.5
Ex. 15	2	3	30	8	22.5
Ex. 16	2	5	52.5	-	-
Ex. 17	2	5	30	7	22.5
Ex. 18	2	5	30	8	22.5
Ex. 19	2	1	30	2	11
	2			9	11.5
Comp. Ex. 1	1 and 3	7	89.5	-	-
Comp. Ex. 2	1 and 3	8	89.5	-	-
Comp. Ex. 3	2	7	52.5	-	-
Comp. Ex. 4		8	52.5	-	-

[0046] Table 2 shows the fundamental properties of the polyolefin resin having a cyclic structure used in the present invention.

Table 2 Fundamental properties

Sample No.	Name	Mw	Mn	i.v.	Mw/Mn	Tg
1	MT 845	6250	3350	0.19	1.9	61

EP 0 978 766 B1

(continued)

Sample No.	Name	Mw	Mn	i.v.	Mw/Mn	Tg
2	MT 854	66100	27700	1.39	2.4	66
3	T-745'-MO	6800	3400	<0.25	2.0	78
5	T-745'-CL	12000	3900	<0.25	3.5	76
7	Tafton NE 2155: Polyester resin, Kao Corp.					
8	MC 100: Styrene acrylate resin, NIPPON CARBIDE INDUSTRIES					
9	MT849	40100	22200	0.7	1.8	65
10	T-745	7000	3800	0.19	1.8	68
<p>Tg: Glass transition point</p> <p>Sample No. 1 (MT845), No. 2 (MT854) and No. 9 (MT849) are polyolefin resins of a cyclic structure having a low viscosity, a high viscosity and a medium viscosity, respectively.</p> <p>Sample No. 3 (T-745' -MO) : Prepared by reacting Sample No. 10 (T-745), a bipolymer of ethylene and norbornene, with a peroxide and 7% by weight, based on T-745, of maleic anhydride to introduce carboxyl groups therein.</p> <p>Sample No. 5 (T-745'-CL) : Prepared by neutralizing about 70% of the carboxyl groups of Sample No. 3 (T-745'-MO), which has carboxyl groups introduced therein, with zinc for conversion into an ionomer.</p> <p>Tafton NE 2155: Tg = 65°C</p> <p>MC100: Tg = 69°C, Mw = 53000, Mn = 23000, Mw/Mn = 2.3</p>						

[0047] The toners prepared by the above toner preparation methods 1, 2 and 3 were each placed in a commercially available electrophotographic copier (PC100, Canon Inc.), and subjected to performance test. The results are shown in Table 3.

Table 3

	Fixability 10 copies/min	Image sharpness		Light transmission 624 nm	Anti-spent toner effect	Offset-free properties
		Thin line resolving power	Gray scale			
Ex. 1	○	○	○	○	○	Δ
Ex.2	○	○	○	○	○	○
Ex.3	○	Δ	Δ	Δ	Δ	Δ
Ex.4	⊙	○	○	○	○	Δ
Ex.5	⊙	○	○	○	○	Δ
Ex.6	⊙	○	○	○	○	○
Ex.7	⊙	Δ	Δ	Δ	Δ	○
Ex.8	⊙	○	○	○	○	⊙
Ex.9	○	○	○	-	○	Δ
Ex.10	○	○	○	-	○	○
Ex.11	○	○	○	-	Δ	Δ
Ex.12	○	○	○	-	Δ	Δ
Ex.13	⊙	○	○	-	○	Δ
Ex.14	⊙	○	○	-	○	Δ

EP 0 978 766 B1

(continued)

5		Fixability 10 copies/min	Image sharpness		Light transmission 624 nm	Anti-spent toner effect	Offset-free properties
			Thin line resolving power	Gray scale			
	Ex.15	⊙	○	○	-	○	Δ
	Ex.16	⊙	○	○	-	○	○
10	Ex.17	⊙	○	○	-	Δ	○
	Ex.18	⊙	○	○	-	Δ	○
	Ex.19	⊙	○	○	○	○	⊙
15	Comp. Ex.1	×	Δ	Δ	○	×	×
	Comp. Ex.2	×	×	×	×	×	×
	Comp. Ex.3	×	○	○	-	×	×
20	Comp. Ex.4	×	○	○	-	×	×

[0048] In Examples 1 to 8 and Comparative Examples 1, 2 two methods for toner preparation are employed. However, the toner formulation and the resin skeleton are common, so that the results on the evaluation items are the same.

Evaluation methods and evaluation criteria

1) Fixability

[0049] The toners prepared with the respective formulations were each used for copying onto recycled papers at a copying rate of 10 copies/min at a fixing temperature of 110 to 140°C, with the fixing temperature for each copying cycle being raised by 10°C. The resulting copy samples were rubbed 10 times with an eraser by using an abrasion tester of Southernland. The load during the test was 40 g/cm². The tested samples were measured for the printing density using a Macbeth reflection densitometer. The symbol × was assigned when even one of the measured values at the respective temperatures was less than 65%. The symbol Δ was assigned when the measured values at the respective temperatures were 65% or more but less than 75%. The symbol ○ was assigned when the measured values at the respective temperatures were 75% or more but less than 85%. The symbol ⊙ was assigned when the measured values at the respective temperatures were 85% or more.

2) Image sharpness

[0050] The toners prepared with the respective formulations were each used for copying onto recycled papers. The resulting samples were checked against sample images of Data Quest. The thin line resolving power and gray scale of the copy image were used as bases for evaluation. The symbol × was assigned for a thin line resolving power of 200 dots/inch or less, Δ for a thin line resolving power of 201 to 300 dots/inch, and ○ for a thin line resolving power of 301 dots/inch or more. The ratio of the reflection density of the copy image to the reflection density of the sample image, at each step of the gray scale, was evaluated as × when less than 65%, Δ when 65% or more but less than 75%, and ○ when 75% or more.

3) Light transmission

[0051] The magenta-colored toners prepared with the formulations of the Examples and the Comparative Examples were each used to produce sheet-shaped samples 100 μm thick. The light transmission of each sheet sample was measured using an optical filter having a peak at 624 nm. The light transmittance at 624 nm was evaluated as × when less than 8%, Δ when 8% or more but less than 11%, and ○ when 11% or more.

4) Anti-spent toner effect

[0052] The toner described in each of the Examples and the Comparative Examples and a ferrite carrier of Powdertech

EP 0 978 766 B1

were put in predetermined amounts into a developer box. After the mixture was agitated and triboelectrically treated for 1 week, 5 g of the toner-deposited carrier was weighed. This toner-deposited carrier was put in soapy water to remove the toner electrostatically adhering to the surface. Only the carrier magnetic powder was withdrawn using a magnet. The magnetic powder was immersed in acetone to dissolve and remove the spent toner fused to the surface. A change in the weight after immersion compared with the weight before immersion was evaluated as ○ when less than 0.2%, Δ when 0.2 or more but less than 0.5%, and × when 0.5% or more.

5) Offset-free properties

[0053] The toners prepared with the respective formulations were each used for copying onto recycled papers at a copying rate of 10 copies/min at a fixing temperature of 90 to 180°C, with the fixing temperature for each copying cycle being raised by 10° C. The printing density of the non-image areas of the resulting samples was measured using a Macbeth reflection densitometer. The printing density of 0.2 or less (printing density of paper = 0.15) represented an offset-free state. The difference between the upper limit and lower limit temperatures in the offset-free state was evaluated as × when 0°C, Δ when 1 to 20°C, ○ when 21 to 40° C, and ⊙ when higher than 40° C.

Claims

1. A toner for development of an electrostatically charged image, said toner comprising a binder resin, a colorant, a function imparting agent, and a charge control agent, wherein said binder resin at least contains a polyolefin resin having a cyclic structure, said polyolefin resin having a cyclic structure is composed of a resin or resin fraction having a number average molecular weight (Mn), as measured by GPC, of less than 7,500 and a resin or resin fraction having said number average molecular weight of 7,500 or more, and in said polyolefin resin having a cyclic structure, a resin or resin fraction having an intrinsic viscosity (i. v.) of 0.25 dl/g or more, and a number average molecular weight (Mn) of 7,500 or more and a weight average molecular weight (Mw) of 15,000 or more, as measured by the GPC method, is contained in a proportion of less than 50% by weight based on the entire binder resin.
2. The toner for development of an electrostatically charged image as claimed in claim 1, wherein said binder resin consists of 1 to 100 parts by weight of said polyolefin resin having a cyclic structure, and 99 to 0 parts by weight of other resin comprising one of a polyester resin, an epoxy resin, a polyolefin resin, a vinyl acetate resin, a vinyl acetate copolymer resin, a styrene-acrylate resin and other acrylate resin, a mixture, hybrid polymers or blends of any of them.
3. The toner for development of an electrostatically charged image as claimed in claim 1 or 2, wherein said polyolefin resin having a cyclic structure has at least one polar functional group.
4. The toner for development of an electrostatically charged image as claimed in claim 3, wherein said polyolefin resin having a cyclic structure has at least one polar functional group selected from a carboxyl group, a hydroxyl group and an amino group.
5. The toner for development of an electrostatically charged image as claimed in any one of claims 1 to 4, wherein said polyolefin resin having a cyclic structure is an ionomer.
6. The toner for development of an electrostatically charged image as claimed in any one of claims 1 to 4, wherein said polyolefin resin having a cyclic structure has a crosslinked structure.
7. The toner for development of an electrostatically charged image as claimed in claim 6, wherein said polyolefin resin having a cyclic structure has a structure crosslinked by a diene, ester, amide, sulfide or ether.
8. The toner for development of an electrostatically charged image as claimed in any one of claims 1 to 7, wherein at least one polar wax is used as the function imparting agent.
9. The toner for development of an electrostatically charged image as claimed in claim 8, wherein at least one polar wax selected from amid wax, carnauba wax, higher fatty acids and their esters, higher fatty acid, metallic soaps, partially aponified higher fatty acid esters or higher aliphatic alcohols is used as the function imparting agent.
10. The toner for development of an electrostatically charged image as claimed in any one of claims 1 to 7, wherein at

EP 0 978 766 B1

least one unpolar wax is used as the function imparting agent.

11. The toner for development of an electrostatically charged image as claimed in claim 10, wherein at least one unpolar wax selected from polyolefin wax or paraffin wax is used as the function imparting agent.

12. The toner for development of an electrostatically charged image as claimed in any one of claims 1 to 11, wherein said polyolefin resin having a cyclic structure that constitutes said binder resin contains resins or resin fractions having three or more molecular weight ranges expressed by number average molecular weight (Mn), as measured by GPC, of less than 7500 or more but less than 25000 or more.

Patentansprüche

1. Toner zur Entwicklung eines elektrostatisch geladenen Bilds, enthaltend ein Bindemittelharz, ein Farbmittel, ein funktionsverleihendes Mittel und ein Ladungssteuermittel, wobei das Bindemittelharz mindestens ein Polyolefinharz mit cyclischer Struktur enthält, welches aus einem Harz oder einer Harzfraktion mit einem zahlenmittleren Molekulargewicht (Mn), bestimmt durch GPC, von weniger als 7 500 und einem Harz oder einer Harzfraktion mit einem zahlenmittleren Molekulargewicht von 7 500 oder mehr besteht und in dem Polyolefinharz mit cyclischer Struktur ein Harz oder eine Harzfraktion mit einer intrinsischen Viskosität (i.v.) von 0,25 dl/g oder mehr und einem zahlenmittleren Molekulargewicht (Mn) von 7 500 oder mehr und einem gewichtsmittleren Molekulargewicht (Mw) von 15 000 oder mehr, bestimmt nach der GPC-Methode, in einem Anteil von weniger als 50 Gew.-%, bezogen auf das gesamte Bindemittelharz, enthalten ist.

2. Toner zur Entwicklung eines elektrostatisch geladenen Bilds nach Anspruch 1, wobei das Bindemittelharz aus 1 bis 100 Gewichtsteilen des Polyolefinharzes mit cyclischer Struktur und 99 bis 0 Gewichtsteilen eines anderen Harzes, umfassend ein Polyesterharz, ein Epoxydharz, ein Polyolefinharz, ein Vinylacetatharz, ein Vinylacetat-Copolymerharz, ein Styrol-Acrylat-Harz und ein anderes Acrylatharz, eine Mischung, Hybridpolymere oder Blends von beliebigen dieser Harze, besteht.

3. Toner zur Entwicklung eines elektrostatisch geladenen Bilds nach Anspruch 1 oder 2, wobei das Polyolefinharz mit cyclischer Struktur mindestens eine polare funktionelle Gruppe aufweist.

4. Toner zur Entwicklung eines elektrostatisch geladenen Bilds nach Anspruch 3, wobei das Polyolefinharz mit cyclischer Struktur mindestens eine unter einer Carboxylgruppe, einer Hydroxylgruppe und einer Aminogruppe ausgewählte polare funktionelle Gruppe aufweist.

5. Toner zur Entwicklung eines elektrostatisch geladenen Bilds nach einem der Ansprüche 1 bis 4, wobei es sich bei dem Polyolefinharz mit cyclischer Struktur um ein Ionomer handelt.

6. Toner zur Entwicklung eines elektrostatisch geladenen Bilds nach einem der Ansprüche 1 bis 4, wobei das Polyolefinharz mit cyclischer Struktur eine vernetzte Struktur aufweist.

7. Toner zur Entwicklung eines elektrostatisch geladenen Bilds nach Anspruch 6, bei dem das Polyolefinharz eine durch ein Dien, einen Ester, ein Amid, ein Sulfid oder einen Ether vernetzte Struktur aufweist.

8. Toner zur Entwicklung eines elektrostatisch geladenen Bilds nach einem der Ansprüche 1 bis 7, wobei als funktionsverleihendes Mittel mindestens ein polares Wachs verwendet wird.

9. Toner zur Entwicklung eines elektrostatisch geladenen Bilds nach Anspruch 8, wobei als funktionsverleihendes Mittel mindestens ein unter Amidwachs, Carnaubawachs, höheren Fettsäuren und deren Estern, Metallseifen höherer Fettsäuren, teilverseiften höheren Fettsäureestern oder höheren aliphatischen Alkoholen ausgewähltes polares Wachs verwendet wird.

10. Toner zur Entwicklung eines elektrostatisch geladenen Bilds nach einem der Ansprüche 1 bis 7, wobei als funktionsverleihendes Mittel mindestens ein unpolares Wachs verwendet wird.

11. Toner zur Entwicklung eines elektrostatisch geladenen Bilds nach Anspruch 10, wobei als funktionsverleihendes Mittel mindestens ein unter Polyolefinwachs oder Paraffinwachs ausgewähltes unpolares Wachs verwendet wird.

EP 0 978 766 B1

12. Toner zur Entwicklung eines elektrostatisch geladenen Bilds nach einem der Ansprüche 1 bis 11, wobei das Bindemittelharz bildende Polyolefinharz mit cyclischer Struktur Harze oder Harzfraktionen mit drei oder mehr Molekulargewichtsbereichen, ausgedrückt durch ein zahlenmittleres Molekulargewicht (M_n), bestimmt durch GPC, von weniger als 7 500 oder mehr, aber weniger als 25 000 oder mehr, enthält.

5

Revendications

1. Toner pour le développement d'une image électrostatiquement chargée, ledit toner comprenant une résine de liant, un colorant, un agent d'impression fonctionnel et un agent de contrôle de charge, dans lequel ladite résine de liant contient au moins une résine de polyoléfine ayant une structure cyclique, ladite résine de polyoléfine ayant une structure cyclique se compose d'une résine ou d'une fraction de résine ayant une masse moléculaire moyenne en nombre (M_n), lorsqu'elle est mesurée par GPC, inférieure à 7 500 et d'une résine ou d'une fraction de résine ayant ladite masse moléculaire moyenne en nombre supérieure ou égale à 7 500, et dans ladite résine de polyoléfine ayant une structure cyclique, une résine ou une fraction de résine ayant une viscosité intrinsèque (η_{int}) de 0,25 dl/g ou plus, et une masse moléculaire moyenne en nombre (M_n) supérieure ou égale à 7 500 et une masse moléculaire moyenne en poids (M_w) supérieure ou égale à 15 000, lorsqu'elle est mesurée par GPC, est contenue dans une proportion inférieure à 50 % en poids sur la base de la totalité de la résine de liant.
2. Toner pour le développement d'une image électrostatiquement chargée selon la revendication 1, dans lequel ladite résine de liant se compose de 1 à 100 parties en poids de ladite résine de polyoléfine ayant une structure cyclique, et de 99 à 0 parties en poids d'une autre résine comprenant une parmi une résine de polyester, une résine époxy, une résine de polyoléfine, une résine d'acétate de vinyle, une résine de copolymère d'acétate de vinyle, une résine de styrène et d'acrylate et toute autre résine d'acrylate, un mélange, des polymères hybrides ou des mélanges de l'un quelconque d'entre eux.
3. Toner pour le développement d'une image électrostatiquement chargée selon la revendication 1 ou 2, dans lequel ladite résine de polyoléfine ayant une structure cyclique possède au moins un groupe fonctionnel polaire.
4. Toner pour le développement d'une image électrostatiquement chargée selon la revendication 3, dans lequel ladite résine de polyoléfine ayant une structure cyclique a au moins un groupe fonctionnel polaire choisi parmi un groupe carboxyle, un groupe hydroxyle et un groupe amino.
5. Toner pour le développement d'une image électrostatiquement chargée selon l'une quelconque des revendications 1 à 4, dans lequel ladite résine de polyoléfine ayant une structure cyclique est un ionomère.
6. Toner pour le développement d'une image électrostatiquement chargée selon l'une quelconque des revendications 1 à 4, dans lequel ladite résine de polyoléfine ayant une structure cyclique a une structure réticulée.
7. Toner pour le développement d'une image électrostatiquement chargée selon la revendication 6, dans lequel ladite résine de polyoléfine ayant une structure cyclique a une structure réticulée par un diène, un ester, un amide, un sulfure ou un éther.
8. Toner pour le développement d'une image électrostatiquement chargée selon l'une quelconque des revendications 1 à 7, dans lequel au moins une cire polaire est utilisée en tant qu'agent d'impression fonctionnel.
9. Toner pour le développement d'une image électrostatiquement chargée selon la revendication 8, dans lequel au moins une cire polaire choisie parmi la cire d'amide, la cire de carnauba, des acides gras supérieurs et leurs esters, un acide gras supérieur, des savons métalliques, des esters d'acides gras supérieurs partiellement saponifiés ou des alcools aliphatiques supérieurs est utilisée en tant qu'agent d'impression fonctionnel.
10. Toner pour le développement d'une image électrostatiquement chargée selon l'une quelconque des revendications 1 à 7, dans lequel au moins une cire apolaire est utilisée en tant qu'agent d'impression fonctionnel.
11. Toner pour le développement d'une image électrostatiquement chargée selon la revendication 10, dans lequel au moins une cire apolaire choisie parmi une cire de polyoléfine ou une cire de paraffine est utilisée en tant qu'agent d'impression fonctionnel.

EP 0 978 766 B1

12. Toner pour le développement d'une image électrostatiquement chargée selon l'une quelconque des revendications 1 à 11, dans lequel ladite résine de polyoléfine ayant une structure cyclique qui constitue ladite résine de liant contient des résines ou des fractions de résine ayant trois gammes de masse moléculaire ou plus exprimées par la masse moléculaire moyenne en nombre (M_n), lorsqu'elle est mesurée par GPC, inférieure à 7 500 ou supérieure à 7 500 et inférieure à 25 000 ou supérieure à 25 000.

10

15

20

25

30

35

40

45

50

55